

# RHODORSIL® OILS 48 V 750 TO V 1 000 000

<b>Description</b>	<b>RHODORSIL OILS 48 V 750 to V 1 000 000</b> are polydimethylsiloxane silicone oils with linear chains and reactive hydroxyl endgroups.
<b>Characteristics</b>	<ul style="list-style-type: none"><li>• Appearance..... viscous liquids</li><li>• Colour..... colourless</li><li>• Specific gravity at 25°C, approx..... 0.975</li><li>• Viscosity at 25°C, approx., mPa.s..... 750 to 1 000 000</li><li>• Freezing point, °C, approx..... - 45</li><li>• Miscibility : oils miscible with ether, aromatic and aliphatic hydrocarbons and chlorinated solvents</li><li>• Flash point, (closed cup), °C approx.<ul style="list-style-type: none"><li>- Oils 48 V 750 and V 3 500..... 220</li><li>- Oils 48 V 10 000 and V 20 000..... 270</li><li>- Oils 48 V 50 000 and over..... 280</li></ul></li></ul>
<b>Packaging</b>	<b>RHODORSIL OILS 48 V 750 to V 1 000 000</b> are available in 200 kg containers. Please consult us for other packaging.
<b>Storage and shelf-life</b>	<p><b>RHODORSIL OILS 48 V 750 to V 1 000 000</b> has a shelf life of 18 months from its date of manufacture (the expiry date is shown on the packaging).</p> <p>Bluestar guarantees the product for 12 months from the shipment date, when stored at a temperature below 30°C in its original unopened packaging.</p> <p>Once the packaging has been opened the product must be used as soon as possible.</p>
<b>Safety</b>	Consult the Safety Data Sheet for <b>RHODORSIL OILS 48 V 750 to V 1 000 000</b> .

## RHODORSIL® OILS 48 V 750 TO V 1 000 000

Visit our website [www.bluestarsilicones.com](http://www.bluestarsilicones.com)

### EUROPE

*Bluestar Silicones France*  
21 Avenue Georges Pompidou  
F69486 Lyon Cedex 03  
FRANCE  
Tel. (33) 4 72 13 19 00  
Fax (33) 4 72 13 19 88

### NORTH AMERICA

*Bluestar Silicones USA*  
Two Tower Center Boulevard  
Suite 1601  
East Brunswick, NJ 08816-1100  
United States  
Tel. (1) 732 227 2060  
Fax (1) 732 249 7000

### LATIN AMERICA

*Bluestar Silicones Brasil Ltda.*  
Av. Maria Coelho Aguiar, 215, Bloco G  
-1º Andar  
05804-902 - São Paulo - SP - Brasil  
Tel. (55)-11-37477887

### ASIA PACIFIC

*Bluestar Silicones Hong Kong*  
Trading Co., Ltd.  
29/ F, 88 Hing Fat Street  
Causeway Bay - Hong Kong  
Tel. (852) 3106 8200  
Fax (852) 2979 0241

#### **Warning to the users**

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products. BLUESTAR SILICONES guarantees that its products comply with its sales specifications. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for given use. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorisations. Users are requested to check that they are in possession of the latest version of this document and BLUESTAR SILICONES is at their disposal to supply any additional information.