

BONDERITE BONDERITE L-GP 2404 ACHESON **GRAPHITE DISPERSION IN SOLVENT**

(KNOWN AS DAG 2404)

Issued 7/18/2013

Description

BONDERITE L-GP 2404 ACHESON (known as Dag 2404) is a high quality lubricant additive consisting of superfine graphite particles in mineral spirits. Lubricants diluted with BONDERITE L-GP 2404 ACHESON (known as Dag 2404) are able to form a highly effective graphite film on metal surfaces at temperatures up to 482°C (900°F). It is particularly successful in conveyor chain operation because it penetrates and forms a solid lubricating film over the entire bearing surface as the carrier vaporizes.

Specific advantages offered by lubricants diluted with

BONDERITE L-GP 2404 ACHESON (known as Dag 2404) include:

- Reduced metal-to metal contact
- Nonfreezable
- Effectiveness at extreme temperatures
- Minimum pre-treatment
- High Lubricity
- · Easy application
- · Extremely low residue

BONDERITE L-GP 2404 ACHESON (known as Dag 2404) is noted for extremely low residue formation when mixed with a quality diluent.

FEATURES	BENEFITS
Stable colloidal suspension of graphite	Minimal mixing costs for blending into your finished lubricant
Fine particle size distribution	Provides cost-effective usage in finished lubricant to provide superior lubrication performance, consumer confidence and repeat sales
Lubricating, low friction graphite particles	Superior lubrication extends equipment life, reduces maintenance costs and lubricant intervals
Robust chemical and base oil compatibility	Minimizes formulation costs for achieving stable and effective product

TYPICAL APPLICATONS Conveyer chains Hot zone bearing lubrication Kiln car wheel bearings

Penetrating oils Automotive upper valv assembly additive

The thin graphitic film produced by BONDERITE L-GP 2404 ACHESON (known as Dag 2404) provides near-perfect lubrication for line-belt conveyors used in glass production operations to carry hot bottles to Lehr ovens. The graphite film allows relative motion between the bottle and the conveyor without the formation of "crizzles" or other markings.

Note: When diluted 1:4 (product: diluent) by weight with a mineral seal oil and continually applied by drop apparatus,



BONDERITE BONDERITE L-GP 2404 ACHESON GRAPHITE DISPERSION IN SOLVENT

(KNOWN AS DAG 2404)

BONDERITE L-GP 2404 ACHESON (known as Dag 2404) eliminated frequent chain breakage in an enclosed heat-treat oven by providing the necessary lubrication for the linkage.

Physical Properties: (as supplied)

Lubricating solid Carrier Viscosit Diluent Solid content Particle size Density Flash point Color :processed micrographite :mineral spirits : 11-14 seconds, #4 Ford cup at 25°C (77°F) : mineral spirits, Stoddard solvents or similar hydrocarbons : 10% : 10 minimum : median 2-4 microns by volume : 0.852 kg/l (7.1 lb/gal) @ 25°C (77°F) : 43°C (110°F) : Black

Method of Use:

Surface Preparation

When evaluating **BONDERITE L-GP 2404 ACHESON (known as Dag 2404)** on a bearing application, the bearing surface should be thoroughly cleaned by chemical rinse or any practical method available. The graphite particles must come in contact with the metal for good adhesion and effective lubrication. If cleaning is not feasible, several liberal applications are recommended during the initial break-in period.

Dilution

BONDERITE L-GP 2404 ACHESON (known as Dag 2404) can be diluted with any compatible petroleum product, such as: conventional oils, kerosene, mineral seal oil, mineral spirits, petroleum oil, and Stoddard solvent.

The diluent and dilution ratios are usually finalized on the job. However, typical recommendations for initial evaluations are:

Weight Ratio			
Application	<u>Diluent</u>	(product:diluent)	
Conveyor Chain	Kerosene or	1:50	
(continuous application)	Mineral Seal Oil		
Conveyor Chain (intermittent application)	Kerosene or Mineral Seal Oil	1:20	
Kiln Car Wheel Bearings	Kerosene	1:20	

Application

Agitate or stir **BONDERITE L-GP 2404 ACHESON (known as Dag 2404)** to a uniform consistency before diluting and again just prior to application. **BONDERITE L-GP 2404 ACHESON (known as Dag 2404)** can then be applied by spray, brush, or drip, whichever method is suitable for the job. Overspray and spills are easily cleaned up with detergent solution.





Technical Process Bulletin

BONDERITE L-GP 2404 ACHESON GRAPHITE DISPERSION IN SOLVENT

(KNOWN AS DAG 2404)

Storage/Handling:

Keep container closed when not in use to avoid contamination. See Henkel Material Safety Data Sheet for proper first aid instructions. Shelf life is 12 months from date of qualification under original seal.

Application/Assistance:

Henkel's Application Specialists are available to assist you in production start-up with **BONDERITE L-GP 2404 ACHESON** (known as Dag 2404). Visit our website www.heneklna.com/metals for more information and for the Henkel global location nearest you.

Health and Safety:

Please consult Material Safety Data Sheet

Henkel Corporation | 32100 Stephenson Highway | Madison Heights, MI 48071 PHONE: (248) 583-9300 | FAX: (248) 583-2976 | www.henkelna.com/

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.**

